

# UltraMag®

## CLASSIFICATION

AWS A5.18	ER70S-6	A-Nr	1	Mat-Nr	1.5125
EN ISO 14341-A	G42 3 C 3Si1 / G46 4 M 3Si1	F-Nr	6		
		9606 FM	1		

## GENERAL DESCRIPTION

Solid wire for semi-automatic and automatic welding applications  
 Good feedability, consistent welding performance  
 Very good weldability, stable arc, and low spatter  
 High productivity

## WELDING POSITIONS (ISO/ASME)



PA/1G



PB/2F



PC/2G



PD/4F



PE/4G



PF/3Gu



PG/3Gd

## SHIELDING GASES (ACC. ISO 14175)

M21	Mixed gas Ar+ >15-25% CO <sub>2</sub>
C1	Active gas 100% CO <sub>2</sub>

## APPROVALS

ABS	BV	DNV	GL	LR	TÜV	CE	DB
+	+	+	+	+	+	+	+

## CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si
0.078	1.4	0.85

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	Yield strength	Tensile strength	Elongation	Impact ISO-V(J)	
			(N/mm <sup>2</sup> )	(N/mm <sup>2</sup> )		-30°C	-40°C
Typical values	M21	AW	502	574	28		102
	C1	AW	486	570	29	71	

## EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	Standard	Type
General structural steels	EN 10025	S185, S235, S275, S355
Ship plates	ASTM A131	Grade A, B, D, AH32 to DH36
Cast steels	EN 10213-2	GP240R
Pipe material	EN 10208-1	L210, L240, L290, L360
	EN 10208-2	L240NB, L290NB, L360NB, L360QB, L240MB, L290MB, L360MB, L415MB, L415NB
	API 5LX	X42, X46, X52, X60
	EN 10216-1	P235T1, P235T2, P275T1
	EN 10217-1	P275T2, P355N
	EN 10028-2	P235GH, P265GH, P295GH, P355GH
Boiler & pressure vessel steels	EN 10025 part 3	S275, S355, S420
Fine grained steels	EN 10025 part 4	S275M, S275ML, S355M, S355ML, S420M, S420ML, S460

## PACKAGING AND AVAILABLE SIZES

Diameter (mm)	0.8	1.0	1.2	1.6
5 kg plastic spool S200	X		X	
16 kg spool B300	X	X	X	X
16 kg spool B5300	X	X		
15 kg spool S300	X	X	X	X
250 kg Accutrak® Drum		X	X	
500 kg Accutrak® Drum		X	X	X
Other sizes and packaging on request				

Ultramag® .rev. C-EN29-27/02/19